



Yb-MCOF-35/250-07-0.9-PM

Yb-DOPED LARGE MODE AREA PM FIBER

SOLUTION OVERVIEW


The Yb-MCOF-35/250-PM fibers are designed for M^2 lower than 1.15, making it the perfect choice for applications requiring superior beam quality. Our fiber design features a confined core for selective gain amplification and multi-layer cladding for superior suppression of higher order modes.

FEATURES

- Designed for output M^2 lower than 1.15
- Large core diameter of 35 μm
- Low photodarkening
- High birefringence
- Confined core for selective gain amplification
- Increased differential bending losses

TYPICAL APPLICATIONS

- Material processing
- Frequency conversion
- Biophotonics
- Range finding



MAIN SPECIFICATIONS

OPTICAL PROPERTIES	
Core NA	0.07 \pm 0.01
Cladding NA	> 0.47
Pump guide absorption @ 915 nm	0.9 \pm 0.1 dB/m
Nominal pump guide absorption @ 975 nm	4 dB/m
Birefringence	$\geq 1.4 \times 10^{-4}$
Beam quality factor M^2	< 1.15

PHYSICAL PROPERTIES	
Optical cladding	Multi
Core diameter	35 \pm 3 μm
Silica cladding diameter	250 \pm 5 μm
Coating diameter	390 \pm 20 μm
Cladding geometry	Round
Screen proof tested	≥ 100 kpsi
Recommended coiling diameter	≥ 14 cm
Confined core	Yes
Depressed cladding	Yes

MAIN SPECIFICATIONS CONTINUED

Two versions of this fiber are available. Please refer to the tables below for a comparison of the specifications.

OPTICAL PROPERTIES	Yb-MCOF-35/250-07-0.9-PM	Yb-MCOF-35/250-07-2.5-PM
Core NA	0.07 ± 0.01	0.07 ± 0.01
Cladding NA	>0.47	>0.47
Pump guide absorption @ 915 nm	0.9 ± 0.1 dB/m	2.5 ± 0.5 dB/m
Nominal pump guide absorption @ 975 nm	4 dB/m	10 dB/m
Birefringence	≥ 1.4 x 10 ⁻⁴	≥ 1.4 x 10 ⁻⁴
Beam quality factor M ²	<1.15	<1.15

PHYSICAL PROPERTIES	Yb-MCOF-35/250-07-0.9-PM	Yb-MCOF-35/250-07- 2.5-PM
Optical cladding	Multi	Multi
Core diameter	35 ± 3 μm	35 ± 3 μm
Silica cladding diameter	250 ± 5 μm	250 ± 5 μm
Coating diameter	390 ± 20 μm	390 ± 20 μm
Cladding geometry	Round	Round
Screen proof tested	≥ 100 kpsi	≥ 100 kpsi
Recommended coiling diameter	≥ 14 cm	≥ 14 cm
Confined core	Yes	Yes
Depressed cladding	Yes	Yes

CONTACT US

1 866 657-7406 | info@ino.ca

ino.ca



© 2022 INO. All rights reserved

Québec (Head Office)
2740 Einstein Street
Québec (Québec) G1P 4S4
CANADA
418 657-7006

Montréal
405 Ogilvy ave, Suite 101
Montréal (Québec) H3N 1M3
CANADA
438 387-8957

Hamilton
175 Longwood Road South, #316 A
Hamilton (Ontario) L8P 0A1
CANADA
905 529-7016

